

Dielectric properties of Ni-Al nano ferrites synthesized by citrate gel method

K.S. Nagaraju¹ and D. Ravinder^{2*}

¹Department of Physics, Vivakananda Degree College, Malleswaram, West Post, Bangalore-560055, Karnataka, India

^{2*}Department of Physics, Osmania University, Hyderabad- 500 007, Telangana, India

ABSTRACT

Ni-Al ferrite with composition of $\text{NiAl}_x\text{Fe}_{2-x}\text{O}_4$ ($x=0.2, 0.4, 0.6,$ and $0.8,$) were prepared by citrate gel method. The Dielectric Properties for all the samples were investigated at room temperature as a function of frequency. The Dielectric constant shows dispersion in the lower frequency region and remains almost constant at higher frequencies. The frequency dependence of dielectric loss tangent ($\tan\delta$) is found to be abnormal, giving a peak at certain frequency for mixed Ni-Al ferrites. A qualitative explanation is given for the composition and frequency dependence of the dielectric loss tangent.

Keywords: Ferrites; Citrate method; lattice parameter; dielectric constant; dielectric loss

I. INTRODUCTION

Ni-Al ferrite is a well-known spinel magnetic material. In the inverse spinel structure of NiFe_2O_4 , the tetrahedral sites are occupied by ferric ions and octahedral sites by ferric and nickel ions. $\text{Ni Al}_x\text{Fe}_{2-x}\text{O}_4$ ferrites are ferrimagnetic materials with a large number of technological applications in telecommunications and entertainment electronics. Ni Al ferrites are among the most widely used soft magnetic materials because of high frequency applications as they possess high electrical resistivity and low eddy current losses [1-3]. It is known that magnetic properties of ferrites are sensitive to preparation technique and their microstructures [4]. The electrical and magnetic properties of such ferrites depend strongly on distribution of cations at the tetrahedral (A) and octahedral [B] sites in the lattice [5 -7]. It is well known that zinc ions can be used to alter the saturation magnetization. It is believed that the addition of zinc ions also affects the lattice parameter and it would therefore be expected to change the Curie temperature of the material [8]. The substitution of divalent ions in pure ferrites leads to the modification of the structural, electrical and magnetic properties [9]. The conventional solid-state reaction route is widely used for the production of ferrite because of its low cost and suitability for large scale production. The citrate method is used to speed up the synthesis of complex materials. It is a simple process, which offers a significant saving in time and energy consumption over the traditional methods. Several researchers have reported the synthesis of Ni-Zn ferrites using different techniques like, refluxing process [10], ceramic

[11], hydrothermal [12], combustion [13], coprecipitation [14], reverse micelle process [15], spark plasma sintering [16], micro emulsion [17] and ball milling etc.

In this work, we present the results of systematic doping of non-magnetic Al content on the dielectric properties of Ni ferrite synthesized by citrate method.

II. EXPERIMENTAL

The starting materials were nickel nitrate, zinc nitrate, iron nitrate, citric acid and ammonia all of analytical grade. The solution of nickel nitrate ($\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$), ferric nitrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$) and Aluminium nitrate ($\text{Al}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$) in their stoichiometry were dissolved in a deionized water. Citric acid was then added to the prepared aqueous solution to chelate Ni^{2+} , Al^{3+} and Fe^{3+} in the solution. The molar ratio of citric acid to total moles of nitrate ions was adjusted at 1: 3. The mixed solution was neutralized to pH 7 by adding ammonia (NH_3) solution. The neutralized solution was evaporated to dryness by heating at 100°C on a hot plate with continuous stirring, until it becomes viscous and finally formed a very viscous gel. Increasing the temperature up to 200°C led to ignition of gel. The dried gel burnt completely in a self propagating combustion manner to form a loose powder. Finally the burnt powder was calcined in air at temperature of 1000°C for one hour to obtain spinel phase. Afterwards the powder was pressed into pellets of thickness 3 mm and a diameter of 10 mm with press by applying a pressure of 2 tons/in². The final sintering was done at 1000°C , afterwards the pellets were coated with silver paint for better electrical contact to measure

the dielectric properties. The dielectric data are measured by Impedance Analyser at room temperature in the frequency range 1 MHz to 13MHz.

III. RESULTS AND DISCUSSIONS

3.1 Dielectric constant with frequency:

The effect of frequency on the dielectric constant (ϵ') can be seen from Figs. 1 to 4 and that the value of dielectric constant decreases continuously with increasing frequency. The decrease in the values of dielectric constant as the frequency increases can be due to electron exchange interaction between Fe^{2+} and Fe^{3+} ions, which cannot follow the alternating electric field. The decrease of dielectric constant with increase of frequency as observed in the case of Ni-Al ferrite. A similar behavior was also observed in [18-21] of various ferrite systems. The explanation for the decrease in the values of ϵ' as the frequency increases can be related to electron exchange interaction between Fe^{2+} and Fe^{3+} ions which cannot follow the alternation of the electric field beyond a certain frequency.

3.2 Dielectric loss tangent ($\tan \delta$) with frequency:

The variation of $\tan \delta$ with frequency can be seen from Figs. 5 to 8, it can be seen from the figures that in the case of Ni-Al nano ferrites. A qualitative explanation can be given for the occurrence of the maxima in $\tan \delta$ versus frequency curves in Ni-Al as pointed out by Iwachi [22], there is a strong correlation between the conduction mechanism and the dielectric behavior of ferrites. The conduction mechanism in n-type ferrites is considered as due to hopping of electrons between Fe^{2+} and Fe^{3+} situated on the octahedral sites. As seen, when the hopping frequency is nearly equal to that of external applied electric field a maximum of loss tangent may be observed [23]. As such it is possible that in the case of Ni-Al nano ferrites the hopping frequencies are of the approximate magnitude to observe a loss maximum at 8 MHz respectively

IV. CONCLUSIONS

It may be concluded that a series of Ni-Al ferrite with compositional formula $\text{NiAl}_x\text{Fe}_{2-x}\text{O}_4$ where $x=0.2, 0.4, 0.6, \text{ and } 0.8$, are prepared by citrate gel method. The lattice constant was found to increase with zinc composition. The variation of dielectric constant and dielectric loss tangent was explained on the basis of electronic exchange between Fe^{2+} and Fe^{3+} ions

ACKNOWLEDGMENTS

One of the KSN is grateful to Prof. G.K. Narayan Reddy, President of JES And former Vice-Chancellor of Karnataka University and Dr. Manchegowda, Honorary Secretary, JES.

REFERENCES

- [1]. X. He, G. Song, J. Zhu, Materials Letters. 59 (2005) 1941-1944.
- [2]. Y. Matsuo, M. Inagaki, T. Tomozawa, F. Nakao, IEEE Trans. Magn. 37 (2001) 2359-2361.
- [3]. P.S. Anil Kumar, J.J. Shrotri, S.D. Kulkarni, C.E. Deshpande, S.K. Date, Mater. Lett. 27 (1996) 293-296.
- [4]. H. Su, H. Zhang, X. Tang, Y. Jing, Y. Liu, J. Magn. Magn. Mater. 310 (2007) 17-21.
- [5]. J.L. Dormann, M. Nogues, J. Phys.: Condens. Matter. 2 (1990) 1223-1237.
- [6]. N. Rezlescu, E. Rezlescu, C. Pasnicu, M.L. Craus, J. Phys. Condens. Matter. 6 (1994) 5707-5716.
- [7]. A.E. Virden, K. O'Grady, J. Magn. Magn. Mater. 290-291 (2005) 868-870.
- [8]. A.M. El-Sayed, Ceramics. Int. 28 (2002) 363-367.
- [9]. Z. Zhong, Q. Li, Y. Zhang, H. Zhong, M. Cheng, Y. Zhang, Powder Technology. 155 (2005) 193-195.
- [10]. A. Dias, R.L. Moreira, Materials Letters. 39 (1999) 69-76.
- [11]. S. E. Jacobo, S. Duhalde, H.R. Bertorello, J. Magn. Magn. Mater. 272-276 (2004) 2253-2254.
- [12]. S.D. Shenoy, P.A. Joy, M.R. Anantharaman, J. Magn. Magn. Mater. 269 (2004) 217-226.
- [13]. S. A. Morrison, C. L. Cahill, E. E. Carpenter, S. Calvin, R. Swaminathan, M. E. McHenry, V. G. Harris, J. Appl. Phys. 95 (2004) 6392-6395.
- [14]. J. Sun, J. Li, G. Sun, W. Qu, Ceramics International. 28 (2002) 855-858.
- [15]. A. Verma, T.C. Goel, R.G. Mendiratta, M.I. Alam. Mat. Sci. Engg. B60 (1999) 156-162.
- [16]. G. Pozo Lopez, S.P. Silveti, S.E. Urreta, E.D. Cabanillas. Physica B. 398 (2007) 241-244.
- [17]. C. Upadhyay, D. Mishra, H.C. Verma, S. Anand, R.P. Das. J. Magn. Magn. Mater. 260 (2003) 188-194.
- [18]. S. Mahalakshmi, K. Srinivasa Manja J. alloys. comp 457 (2008) 522-525
- [19]. D. Ravinder, J. Vijaya Bhasker Reddy, Mater. Lett. 57 (2003) 4344-4350

- [20]. N.Rezlescu, E.Rezlescu, Slid state Commun, 14(1974)69.
- [21]. V.R.Murthy, J.Sobbhandari, phys.Stat.sol(A) 36(1976)K133
- [22]. K.Iwauchi Japan.J.Appl.Phys.10(1971)1520
- [23]. A.M Abdeen, O.M Hemed, E.E Assem, M.M. EI-sehly, J.Magn.Magn.Mater238(2008)75




Figure 1 – Dielectric constant Vs Frequency




Figure 2 – Dielectric constant Vs Frequency




Figure 3 – Dielectric constant Vs Frequency




Figure 4 – Dielectric constant Vs Frequency




Figure 5 – Dielectric loss tangent Vs Frequency




Figure 6 – Dielectric loss tangent Vs Frequency




Figure 7 – Dielectric loss tangent Vs Frequency




Figure 8 – Dielectric loss tangent Vs Frequency