

Influence of Mechanical Properties by Addition of Nickel & Silicon to AA6061 Fabricated By Stir Casting For Aluminium Flange Applications

N.Prashanth¹, L. Radhakrishna²

1 M.tech Student , Department of Mechanical Engineering, S R Engineering College, Warangal, Telangana, India.

2 Assistant Professor, Department of Mechanical Engineering, S R Engineering College, Warangal, Telangana, India.

Corresponding Author: N.Prashanth

ABSTRACT:

The proposed work is to analyse the hardness and tensile properties of aluminium alloy AA6061 reinforced with the silicon carbide, aluminium oxide and zirconium oxide to improve the strength of piston material. There will be several failures occurring in the piston due to continuous working. Therefore need arises to develop new material which will satisfy the requirement of modern engine Super high-strength aluminium alloys AA6061&Ni have attracted much attention in the aerospace fields due to their excellent combination of low density and high-strength Recently, attempts, including a chemical composition modification for an AA6061 and Ni alloy and employing new heat treatments, were made to further increase the properties of these alloys. The present work involves the effects of nickel and silicon addition on the strength hardness and impact strength of AA6061 alloys were investigated. With the change in the composition of Ni as 2.0% and Si as 1.5% & 2.0% investigated by conducting tests strength, hardness, and impact strength of AA6061.

Keywords: AA6061, Ni, Si, Aluminium, alloys, matrix composites, high temperature.

I. INTRODUCTION:

Aluminium alloy as well as their steel matrix compounds has actually located application in the production of numerous vehicle engine parts such as cylindrical tube blocks and also pistons. Nevertheless, many Al based alloys are not ideal for heat applications. However the AA6061 steel matrix compounds must be lugging temperature level is minimally boosted as much as 650 to 700 of melting factor. The pistons for high-speed engine are mainly produced aluminium alloys which including the support of products to enhancing the firmness and also temperature level buildings. New modern technology advancements and also the execution of producing procedures that adds to the manufacturing of lasting items, solutions and also job methods. The main emphasis of the research study is to recognize the influence of sustainability campaigns on labour force growth. Polymer matrix compounds provide makers the possibility to produce lighter, more powerful as well as even more deterioration immune items boosting conductivity as well as resilience of items as well as inevitably favourably affecting production as well as industrial success. Compounds are categorized according to their matrix stage. Therefore, there are ceramic matrix compounds (CMCs), polymer matrix compounds (PMCs), and also steel matrix compounds

(MMCs). Products within these groups are usually called "progressed".

if they display buildings, such as heat toughness or high rigidity each weight, that are substantially far better than those of even more standard architectural products, such as steel and also light weight aluminium. Such residential or commercial properties make it feasible to construct composite frameworks having the very same stamina as well as tightness as steel frameworks yet with as much as 50 percent much less weight, a significant benefit in airplane as well as room applications. MMCs normally contain a low-density steel such as light weight aluminium or magnesium strengthened with particle or fibers of a ceramic product, such as silicon carbide or graphite. Compared to the unreinforced steel, MMCs have dramatically higher rigidity and also stamina nevertheless, these homes are acquired at the price of reduced ductility as well as durability Current markets for MMCs are mainly in army as well as aerospace applications. Speculative MMC parts have actually been created for usage in airplane, jet engines, and also projectiles. MMC products with high details rigidity as well as stamina might be utilized in applications in which a vital element is lowering weight. Consisted of in this group are land-based cars, airplane, ships, as well as high-speed equipment.

II. RELATED STUDY:

Super high-strength light weight aluminium alloys (Al-Zn-Mg-Cu) have actually drawn in much interest in the aerospace areas as a result of their exceptional mix of reduced thickness and also high stamina [1, 2] Lately, efforts, consisting of a chemical structure alteration or an Al-Zn-Mg-Cu alloy and also utilizing brand-new warm therapies, were made to more rise the buildings of these alloys. Zhao as well as Tsuchida [3] located that including chromium (Cr) or zirconium (Zr) right into AA 7075aluminum alloy can prevent the grain coarsening. Chaubey et al. [4] observed that an enhancement of cerium (Ce) right into Al-Zn Mg-Cu alloy has actually led to approximately 5% grain improvement of the actors dendritic framework along with approximately 38% improvement of heat-treated microstructure. Nonetheless, the applications of the rare-earth steels had in light weight aluminium alloys are exceptionally limited as a result of their high expense. Consequently, even more focus has actually been paid to the change steels which are affordable such as nickel. Previous study revealed that nickel plays an vital function in strong service conditioning as well as can successfully boost the mechanical homes of Al-7Si alloys [5] Farkoosh et al. [6] evaluated the stage development in an Al-Si-Cu-Mg-Ni alloy with including nickel (0-1 wt.%); additionally, the Al₃CuNi stage has higher impact on the total toughness of the alloy contrasted to various other Ni-bearing speeds up.

Al-- Si piston alloy base compounds strengthened with various mixes of Ni and also nano-Al₂O₃ bits have actually been produced by press spreading and also their metallurgical as well as mechanical characterization has actually been checked out. (Abdelaziz, 2014). The result of alloying components on mechanical practices of Al12 mass % Si casting alloys for piston has actually been done. The impact of substances attributes on the heat mechanical efficiency came to be much more obvious to lessen the flaws (Chang- Yeol Jeong, 2012). The spreading product of the here and now job will certainly be Aluminium Silicon scraps of piston. Metal mould strategy is made use of for spreading of piston. The liquefied product gotten ready for piston in called for make-up is put to the tooth cavity to obtain wanted form of the piston (Francis Uchenna Ozioko, 2012). This research study displays the powder building of aluminium alloy for piston product by the make-up of products, perform layout by FEM simulation, cool compaction of aluminium alloy powder as well as carry out sintering. The residential or commercial properties like toughness, firmness were contrasted in

between recently created piston and also existing casted piston (Hyos Lee, 2001). This write-up stands for the enhanced compound and also enhanced alloy of fixed architectural attributes of a piston under gas stress force and also inertia pressure (Prakash Gadade, 2013). The research study examination reveals the warmth therapy impact of microstructure and also mechanical homes of non-aluminium alloys made use of for piston production.

III. DESIGN AND METHODOLOGY:

The technique of the recommended job is executed making use of the mix casting method under ideal factors to consider as a result of the budget-friendly technique when contrasted to all various other approaches. The construction of product by utilizing the mix spreading approach. Production technique is made from the raw product rather than currently existing product. The steel manufacture is finished with the significant requirements of the heating system temperature level. The stirrer rate is kept frequently as well as the preheating of product to be done prior to the procedure. The steel melting temperature level needs to be preserved continuously for all the examples. The stirrer timing is kept frequently for all the examples. The made sampling from the procedure utilizing die will certainly be prepared according to ASTM conventional dimension. Machining procedure needs to be done after the favoured dimension sampling for making the examination.

Al And NI & SI adding percentage indication:

Al	Mg	Si	Fe	Cu	Mn	Cr	Zn	Ti	Element
Remains	0.8-1.2	0.4-0.8	0-0.7	0.15-0.4	0-0.15	0.04-0.35	0.25	0.15	composition

Ni	Fe	Cobalt	Element
Remains	0.1	0.005	Composition

Si	All other(max)	O ₂	Element
Remains	0.1	0.3-0.4	composition

Adding Procedure:

Production of light weight aluminum alloy based casting composite products through mix spreading is among the noticeable as well as

affordable path for advancement and also handling of steel matrix compounds products. Residences of these products rely on several handling specifications and also option of matrix as well as supports. There are numerous specifications in this procedure, which impact the last microstructure and also mechanical residential or commercial properties of the compounds. In this research, micron-sized Ni & Si fragments were utilized as support to make Al-2.0 wt% Ni-1.5 wt% Si and also Al-2.0 wt% Ni-2.0 wt% Si compounds at casting temperature levels (850°C) and also mixing durations (2 as well as 6 minutes).

Mix casting procedure begins with positioning vacant crucible in the muffle. Initially heating system temperature level is readied to 500 ° C and after that it is progressively raised as much as 900 ° C. High temperature level of the muffle assists to thaw aluminum alloy swiftly, lowers oxidation degree. Fee computations adhering to guidelines were used to approximate the quantity of the Al 6061 billets and also Ni & Si needed to create 2.0 and also 1.5 & 2.0 weight percents (wt.%) Ni & Si supports in the compound.



Fig.3.1. Procedure of adding chemicals.

IV. EXPERIMENTAL RESULTS:

An outside temperature level probe was made use of in all instances to keep track of the temperature level analyses of the heater. After the hand-operated mixing, the composite slurry was reheated as well as preserved at a temperature level of 850° C +/- 10° C (over the liquidus temperature level) and afterwards mechanical mixing was done. The mixing procedure was executed for 6 mins at an ordinary mixing price of 400rpm. Casting was after that carried out on ready sand moulds at a putting temperature level of 720° C. Composite slurry is gathered the metal mould. Mould is pre-heated at temperature level 500 ° C prior to putting of the liquefied slurry in the mould.



Fig.4.1. Metallic Mould

Testing:

1.A tensile examination, additionally called stress examination is a mechanical examination that can be done on products. Tensile examination is reasonably easy, cost-effective as well as totally standard. In this examination, an example undergoes a stress till damaging factor or failing of a product. This arise from the examination which were performed are typically utilized to pick a product for an application, for quality assurance, and also to forecast exactly how a product will certainly respond under various other kinds of pressures. A tensile sampling is a standard example cross-section. It has 2 shoulders as well as an area in between. The shoulders are big so they can be easily grasped, whereas the area has a smaller sized cross-section to ensure that the contortion as well as failing can take place in this field.



Fig.4.2. Testing modules.

2. It is a measure of resistance that how resistant solid matter is to vary with change of permanent shape when a compressive force is applied. Some materials, such as metal, are harder than others. Hardness is dependent on ductility, elastic stiffness, plasticity, strain, strength, toughness, viscoelasticity, and viscosity. In our project we used Brinell's & Rockwell Hardness Test.



Fig.4.3.1. Brinell's test specimens.



Fig.4.3.2. Rockwell test specimens.

3. In mechanics, an impact is a high force or shock applied over a short period of time when two or more bodies collide. Such a force or acceleration usually has a greater effect than application of lower force over a proportionally longer period of time. This effect depends critically on the relative velocity of bodies with one another. Charpy test is also known as the V-notch test, is a standardized high strain-rate test which determines the amount of energy absorbed by a material during fracture.



Fig.4.4. Testing work pieces.

When contrasted to the base steel alloy the stamina of 2.0 wt% Ni & 1.5 wt% Si included composite is raised. When we include Ni to Al the strong solubility of Ni in AA6061 does not surpass 0.04%. Over this quantity it exists as an insoluble intermetallic normally in mix with Iron These intermetallic substances slow down the grain development, bring about grain improvement, as well as lead to more strengthening impacts. When

contrasted to the 2.0 wt% Ni & 2.0 wt% Si the stamina reduced considerably this is since as the Ni web content boosts the intermetallics rises. Rise in intermetallics lowers the general toughness of the compound because of this the stamina reduces The electro negativness of Al is 1.6 which of Ni is 1.967 the distinction in the electro negativness triggers the development of ionic bond The portion of prolongation of the steel boosts when we include 2.0 wt% of Ni & 1.5 wt% of Si And minimizes significantly when we enhance % of Si to 2.0 wt% with exact same % of Ni The influence power likewise enhances when we include upto 2.0 wt% Ni & 1.5 wt% Si and also lowers if we boost the wt% of Si to 2.0 wt% at the very same wt% of Ni.

MATERIAL/ PROPERTY	AA 6061	AA 6061 and 2.0wt% NICKEL & 1.5wt% SILICON	AA 6061 and 2.0wt% NICKEL & 2.0wt% SILICON
ULTIMATE TENSILE STRENGTH	124.290 MPa	113.744 MPa	103.767 MPa
HARDNESS (BRINELL'S)	47.5HBW/5/250	57.56HBW/5/250	53.46HBW/5/250
HARDNESS (ROCKWELL)	60	68.75	66.5
IMPACT ENERGY	30 JOULES	38 JOULES	49 JOULES

Fig.4.5. Comparison of all tests for adding chemicals.

V. CONCLUSION:

As the percent of Ni boost to 2.0 wt% and also 1.5 wt% of Si the residential properties like Hardness and also Impact power are rises contrasted to base AA6061.If even more we boost the Si material to 2.0 wt% there is a modest decrease in the homes contrasted to base AA 6061. By this we understand that enhancement of Ni to AA 6061 as much as particular quantity (0.4%) boosts the homes past that there is a modest decrease in the residential properties like toughness, solidity as well as effect power.

By the constant disperse of splendid particles are presenting of Silicon in structure. However, when the primary silicon appears micro particles, the strength properties decrease with increasing silicon content, but the hardness goes on increasing because of the increase in the number of silicon particles.

REFERENCES:

- [1]. K. Sagar and L. Radhakrishna, "The Influence of Nickel Addition on the Mechanical Properties of AA6061 Fabricated By Stir Casting." *International Journal of Materials Science* ISSN 0973-4589 Volume 12, Number 4 (2017), pp. 617-625
- [2]. L. Huang, K. Chen, and S. Li, "Influence of grain-boundary pre-precipitation and corrosion characteristics of inter-granular phases on corrosion behaviors of an Al-Zn-Mg-Cu alloy," *Materials Science and Engineering B*, vol. 177, no. 11, pp. 862–868, 2012.
- [3]. C. Feng, Z. Liu, A. Ning, and S. Zeng, "Effect of low temperature aging on microstructure and mechanical properties of super high strength aluminum alloy," *Journal of Central South University of Technology*, vol. 13, no. 5, pp. 461–467, 2006.
- [4]. P. Z. Zhao and T. Tsuchida, "Effect of fabrication conditions and Cr, Zr contents on the grain structure of 7075 and 6061 aluminum alloys," *Materials Science and Engineering A*, vol. 499, no. 1-2, pp. 78–82, 2009.
- [5]. Francis Uchenna Ozioko, *Casting of Motorcycle Piston From Aluminium Piston Scrap Using Metallic Mould*, Leonardo Electronic Journal of Practices and Technologies, 2012.
- [6]. X.-G. Dong, J. Zhou, Y.-J. Jia, and B. Liu, "Effect of alloying on high temperature fatigue performance of ZL114A (Al-7Si) alloy," *Transactions of Nonferrous Metals Society of China*, vol. 22, supplement 3, pp. s661–s667, 2012.
- [7]. Hyos Lee, Jae S. Yeo, Soon H. Hong, *transactions*, 53 (1), 2012.
- [8]. Duk J. Yoon, Kyung H. Na, *The Fabrication Process and Mechanical Properties of SiCp/Al-Si metal Matrix Composites for Automobile Air-Conditioning Compressor Pistons*, *Journal of materials processing technology*, 113, 2001.
- [9]. Y. Wu, F.H. Froes, C. Li, and A. Alvarez, "Microalloying of Sc, Ni, and Ce in an advanced Al-Zn-Mg-Cu alloy," *Metallurgical and Materials Transactions A*, vol. 30, no. 4, pp. 1017–1024, 1999.
- [10]. 1. Dieter, *Mechanical Metallurgy*, McGrawHill.
- [11]. Dowling E.D., *Mechanical Behavior of Materials*, Prentice-Hall.
- [12]. Kayal B S, Ensari C. and Dikey F., *Metalik Malzemelerin Mekanik Deneylemi*, DTÜ Yayınları

N.Prashanth" Influence of Mechanical Properties by Addition of Nickel & Silicon to Aa6061 Fabricated By Stir Casting For Aluminium Applications" *International Journal of Engineering Research and Applications (IJERA)*, Vol. 09, No.05, 2019, pp. 42-46